

MasterRoc[®] MG 04

High early strength, high yield, thixotropic cable bolt grout

MATERIAL DESCRIPTION

MasterRoc MG 04 is a high early strength, thixotropic grout for placement of cable and rock bolts in underground mine and civil tunnel applications. **MasterRoc MG04** is high yield and shrinkage compensated with an extended working time.

AREAS OF APPLICATION

MasterRoc MG 04 is designed for use in the post-grouting of roof bolts and cable anchors where the “top-down” grouting method is preferred.

MasterRoc MG 04 has been developed to provide high early and long-term strengths with an extended working time. **MasterRoc MG 04** allows for early re-entry times without flash-setting in the mixing bowl.

The grout is recommended for the latest generation of cable bolts.

CHARACTERISTICS AND BENEFITS

- High early strength development (35MPa @ 4h) for early re-entry times for critical path installations
- Extended working time (60 minutes at 32°C) enabling easier clean-up of pumps and hoses.
- Extremely pumpable but shows rapid thixotropy to restrict flow into surrounding strata.
- Eliminates the requirement for sealing of the collar and plate with cotton waste etc.
- Good ultimate strength to ensure the permanence and safety of critical installations.
- Shrinkage compensated for greater bond strength to surrounding strata.
- High bond to steel.

PERFORMANCE CHARACTERISTICS

Grout strength development is dependent on amount of mixing water, ambient temperature, age and curing. Typical rates of compressive strength development for **MasterRoc MG04** at the recommended water to product ratio under controlled laboratory conditions are shown below:

MasterRoc MG 04 Compressive Strength (MPa) – 4L water per 20kg bag

Time	Typical Result (MPa)
2 hours	10
4 hours	35
24 hours	55
7 days	65
28 days	80

MIXING EQUIPMENT

Master Builders Solutions recommend using a high shear paddle mixer with accurate water dosing measurement.

MIXING

MasterRoc MG 04 is supplied in a ready to use form requiring only the addition of clean potable water. Do not use hardened or lumpy grout caused by torn or water damaged bags.

Fill mixer with correct volume of water to match number of bags of **MasterRoc MG 04**. A good mixer should have a method of accurately determining water content.

Start the mixer and slowly add **MasterRoc MG 04** powder. Continue mixing the grout until a thick creamy, no-lump consistency is obtained.

Actual amount of water will depend on the desired consistency of the grout required and the grout pump available. As a guide, use 4 litres per 20kg bag.

Do not use excess water (above 4.2 litres for thixotropic mixes). Discard any grout that has been left in excess of 60 minutes. Do not re-temper.

PLACEMENT – “THICK MIX” METHOD

MasterRoc MG 04 can be pumped with a piston ump. The grout is pumped into a drilled bore hole via the grout tube, which extends to the top of the hole. Grouting continues until the **MasterRoc MG 04** completely fills the bore hole, encasing the cable or roof bolt and can be seen emitting past the plate under pump pressure.

Where broken or loose strata is encountered, the grouts thixotropic consistency restricts flow into the voids and pockets effectively sealing off the bore hole, minimising grout loss (grouting methodology varies according to the type of anchor being used).

CLEANING

As with all grouting operations, systematic cleaning of the pump and grout lines with clean water is essential. This should be done immediately after completion of grouting operations. If delays occur greater than 60 minutes, the batched grout should be discarded and the pump and grout lines cleaned.

ESTIMATING DATA

20kg of **MasterRoc MG 04** mixed with 4 litres of water will yield approximately 11 litres.

PACKAGING

MasterRoc MG 04 is packaged in 20kg bags.

SHELF LIFE

Pallets should be stored in a dry place. **MasterRoc MG 04** has a shelf life of 12 months.

MasterRoc[®] MG 04

High early strength, high yield, thixotropic cable bolt grout

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Safety Data Sheet (SDS) from our office or website.

DISCLAIMER

MasterRoc-MG04 -ANZ-V4-0221

STATEMENT OF RESPONSIBILITY The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

NOTE Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a

<p>MB Solutions Australia Pty Ltd ABN 69 634 934 419 11 Stanton Road Seven Hills NSW 2147</p> <p>Freecall: 1300 227 300 www.master-builders-solutions.com/en-au</p>	<p>MB Solutions New Zealand Ltd 45C William Pickering Drive Albany, Auckland New Zealand</p> <p>Freecall: 0800 334 877</p>	<p>Emergency Advice: 1300 954 583 within Australia (24hr) 0800 001 607 within New Zealand</p>
--	---	--